

INTAMSYS[®] PEEK

INTAMSYS® PEEK is a high performance thermoplastic, **P**olyEtherEtherKetone (PEEK). It is semi crystalline, FDA food contact compliant. It offers high strength and stiffness as well as high heat resistance. Also, chemically resistant to aggressive environments, suitable for sterilisation for medical and food contact applications.

| PHYSICAL PROPERTIES | TEST METHOD | UNITS | TYPICAL VALUE |
|---|-----------------------|-------------------------------|-----------------|
| Density | ISO 1183, Crystalline | g/cm ³ | 1.30 |
| Glass transition temperature | ISO 11357 | °C | 143 |
| Melting Point | ISO 11357 | °C | 343 |
| Heat Deflection Temperature | ISO 75-f, 1.8 MPa | °C | 152 |
| Thermal Conductivity | ISO 22007-4, 23°C | $W\ m^{{}_{-1}}\ K^{{}_{-1}}$ | 0.29 |
| Melt index | ISO 1133, 380°C, 5 kg | g/10min | 10 |
| Shore D Hardness | ISO 868, 23°C | - | 85 |
| Water Absorption by immersion (3.2mm | ISO 62-1, 24h, 23°C | % | 0.07 |
| thick Tensile Bar) | Equilibrium, 23°C | % | 0.4 |
| Odor | - | - | Almost odorless |

| MECHANICAL PROPERTIES | TEST METHOD | UNITS | TYPICAL VALUE |
|-----------------------|-------------|-------------------|---------------|
| Tensile strength | ISO 527 | MPa | 99.9 |
| Young's modulus | ISO 527 | MPa | 3738 |
| Elongation at break | ISO 527 | % | 9.1 |
| Bending strength | ISO 178 | MPa | 147.0 |
| Bending modulus | ISO 178 | MPa | 3612 |
| Impact strength | ISO 179 | kJ/m ² | 7.1 |

Disclaimer

The typical values presented in this document are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End-use performance of printed parts properties can be impact by, but not limited to, part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice.

Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of INTAMSYS materials for the intended application. INTAMSYS makes no warranty of any kind, unless announced separately, to the fitness for any particular use or application. INTAMSYS shall not be made liable for any damage, injury or loss induced from the use of INTAMSYS materials in any particular application.